## DATA Sheet

# FP12-5.4

**FULBAT** GENERAL PURPOSE BATTERY

www.fulbat.com - 🙃 FULBAT




NON-SPILLABLE




FP Series are general purpose batteries with 5 years design life in float service. With advanced AGM valve regulated technology and high purity raw material, the FP series batteries ensure high performance and reliable standby service life. They have been designed specifically for applications such as security & alarm systems, UPS, Telecom, power grid, medical equipment and emergency lighting. It can also be used for light cycling use. For intensive cycling, the FPC or FPG cyclic ranges are recommended.

#### **DIMENSIONS & WEIGHT**


LENGHT	90±2mm
WIDTH	70±1mm
TOTAL HEIGHT	107±2mm
WEIGHT	1. <b>65kg</b> (tolerance ± 3%)



TERMINAL (MM)



SPECIFICATION							
Nominal voltage	12V (6 cells)						
Nominal capacity	5.4Ah (20hr)						
Design life	5 years at 20°C						
Internal resistance	Approx 30m Ω						
Terminal	T2						
Max. discharge current	81A (5 sec)						
Reference capacity	5.40Ah     (20hr, 1.80V/cell, 25°C/77°F)       5.02h     (10hr, 1.80V/cell, 25°C/77°F)       4.54Ah     (5hr, 1.75V/cell, 25°C/77°F)       3.96Ah     (3hr, 1.75V/cell, 25°C/77°F)       3.28Ah     (1hr, 1.60V/cell, 25°C/77°F)						
<b>Charge voltage</b> Standby use voltage	13.5V ~ 13.8V 25°C/77°F Temperature compensation: -10mV/°C/Cell						
Cycle use voltage	14.4V ~ 15.0V 25°C/77°F Temperature compensation: -15mV/°C/Cell						
Operating temp. range	Discharge: -15°C ~ 50°C Charge: 0°C ~ 40°C Storage: -15°C ~ 40°C						
Nominal operating temp. range	₂ 25°C ± 3°C / 77°F ± 5°F						
Self discharge	Can be stored for up to 6 months at 25°C/77°F and then recharging is recommended. Monthly self-discharge ratio is less than 3% at 25°C/77°F						
Capacity affected by temp.	40°C/104°F 103% 25°C/77°F 100% 0°C/32°F 86%						
Container material	A.B.S. UL94-HB   UL94-VD optional						



**APPROVALS** 

ISO9001 - Quality management system ISO14001 - Environnmental management System Approved for transport by Air (IATA) Designed in accordance with IEC 60896-21/22



## DATA SHEET

# **FP12-5.4**




www.fulbat.com - 🕶 FULBAT

### CONSTANT CURRENT DISCHARGE (AMPERES) AT 25°C/77°F


F.V/Time	5min	10min	15min	20min	30min	45min	1h	Zh	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	10.4	7.23	5.96	5.17	4.15	3.19	2.61	1.59	1.21	0.998	0.847	0.734	0.583	0.485	0.267
1.80V/cell	12.7	8.62	6.91	5.85	4.59	3.48	2.81	1.69	1.28	1.05	0.883	0.766	0.605	0.502	0.270
1.75V/cell	15.1	9.75	7.62	6.37	4.90	3.69	2.95	1.77	1.32	1.08	0.907	0.785	0.621	0.512	0.273
1.70V/cell	17.1	10.8	8.25	6.84	5.15	3.84	3.08	1.84	1.36	1.11	0.930	0.804	0.630	0.521	0.278
1.65V/cell	18.9	11.6	8.73	7.18	5.37	3.99	3.21	1.89	1.40	1.13	0.950	0.819	0.641	0.528	0.281
1.60V/cell	19.8	12.1	9.09	7.40	5.52	4.08	3.28	1.95	1.43	1.16	0.970	0.835	0.654	0.537	0.283

### CONSTANT POWER DISCHARGE (WATTS/CELL) AT 25°C/77°F

F.V/Time	5min	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	19.6	13.8	11.5	10.0	8.09	6.25	5.14	3.15	2.41	1.99	1.69	1.47	1.17	0.978	0.540
1.80V/cell	23.8	16.3	13.2	11.2	8.89	6.77	5.50	3.33	2.52	2.08	1.76	1.53	1.21	1.01	0.543
1.75V/cell	27.8	18.2	14.4	12.1	9.43	7.16	5.76	3.46	2.59	2.13	1.79	1.55	1.23	1.02	0.544
1.70V/cell	31.2	19.9	15.4	12.9	9.84	7.39	5.97	3.58	2.67	2.17	1.83	1.58	1.25	1.03	0.551
1.65V/cell	33.9	21.1	16.1	13.5	10.2	7.63	6.17	3.66	2.72	2.21	1.86	1.61	1.26	1.04	0.556
1.60V/cell	35.1	21.7	16.6	13.7	10.3	7.72	6.26	3.75	2.77	2.25	1.89	1.63	1.28	1.05	0.556




### **TEMPERATURE EFFECTS IN RELATION TO BATTERY CAPACITY**




Temperature (°C)

### **CYCLE LIFE IN RELATION TO DEPTH OF DISCHARGE**




Testing condition Discharging:current D.17C A(FV 1.7V/cell); Charging:current D.2SC max, voltage 2.4SV/cell; Charging volume:125% of discharged capacity


#### **FLOAT CHARGING CHARACTERISTICS**



**EFFECT OF TEMPERATURE ON LONG TERM FLOAT LIFE** 



#### SELF DISCHARGE CHARACTERISTICS



Storage Times (Months)

No supplementary charge required (carry out supplementary charge before use if 100% capacity is required) B Supplementary charge required before use. Optional charging way as below:
1. Charged for above 3 days at limited current 0.25CA and constant voltage 2.25V/cell

Charged for above 2D hours at limited current D.25CA and constant voltage 2.45V/cell
Charged for 8-1D hours at limited current D.05CA

Supplementary charge may often fail to recover the capacity. The battery should never be left standing till this is reached

